



GUANGZHOU MATEYS CHEMICALS LTD.

CU-200 Copper Immersions Plating Powder

1、 Specifications

- (1) Perfect binding force in a chemical plating on Steel parts
- (2) Suitable for under deposit before piped acid Copper plating
- (3) Easy operation

2、 Composition & Conditions

| Composition | Range |
|--|------------|
| Sulfuric acid(H ₂ SO ₄) | 50-60 ml/L |
| CU-200 | 30-50 g/L |
| Temperature | 40-50°C |
| Time | 0.5-2 min |

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,
Tianhe Dist., Guangzhou, China 510665

TEL: +86 20 85576176/85555261/85555262

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com