



GUANGZHOU MATEYS CHEMICALS LTD.

RNI-5 Nickel Barrel Plating Solution

1、 Specifications

- (1) Bright & white deposit
- (2) Perfect throwing and softening power
- (3) Fast bright & level
- (4) Compact deposit against rusts and yellowish
- (5) Special for Zinc-base alloy parts or parts with more reactions in low area
- (6) High impurities tolerance
- (7) Few organic decomposition
- (8) Easy to maintain

2、 Composition & Conditions

Composition	Standard	Range
Nickelous sulfate($\text{NiSO}_4 \cdot 6\text{H}_2\text{O}$)	250g/L	180—280g/L
Nickel chloride($\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$)	50g/L	40—60g/L
Orthoboric acid(H_3BO_3)	45g/L	35—50g/L
RNI-3A Throwing Agent	10ml/L	8—12ml/L
RNI-3B Main Brightening	0.5ml/L	0.4—0.8ml/L
NI-K Wetter NI-K	2ml/L	1.5—3.0ml/L
pH value	4.2	3.8—4.5
Temperature	55℃	50--60℃
Current Density	1--4A/d m ²	
Voltage	10-15V	
Agitation	Clear air agitation	
Anode Materials	S-Ni plate or electrolytic Nickel plate	
Anode Bag	PP Bag	

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,

Tianhe Dist., Guangzhou, China 510665

TEL: +86 20 85576176/85555261/85555262



GUANGZHOU MATEYS CHEMICALS LTD.

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com