



GUANGZHOU MATEYS CHEMICALS LTD.

SNI-20 High Sulphur Nickel Plating Solution

1、 Specifications

- (1) Be a middle deposit of semi-bright Nickel and bright Nickel
- (2) Strengthen current density to improve corrosion resistance
- (3) Perfect gloss & few brittleness
- (4) S ion reach up to 0.15%
- (5) Up to 160-180mV current density difference with semi-bright Nickel deposit
- (6) Single agent
- (7) Easy to operate
- (8) Stable solution
- (9) Few decomposition
- (10) Long term use

2、 Composition & Conditions

Composition	Range
Nickelous sulfate($\text{NiSO}_4 \cdot 6\text{H}_2\text{O}$)	250-300 g/L
Nickel chloride($\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$)	35-45 g/L
Orthoboric acid(H_3BO_3)	35-40 g/L
SNI-20 Additive	4-6 ml/L
DN-01 Wetter	1-3 ml/L
pH value	2-4
Temperature	40-50°C
Current density	1-6A/dm ²

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,
Tianhe Dist., Guangzhou, China 510665

TEL: +86 20 85576176/85555261/85555262

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com