



GUANGZHOU MATEYS CHEMICALS LTD.

MT-866 Electroless Nickel Plating

1、Specifications

- (1) Special for chemical Nickel deposition
- (2) Used for plastic parts
- (3) Form uniform, compact deposit
- (4) Ni-P alloy deposit on non-metal surface
- (5) Good binding force
- (6) Perfect conductivity
- (7) Easy operation
- (8) Simple maintenance
- (9) Perfect stability

2、Compositions & Conditions

Compositions	Perfect	Range
MT-866Mu	100ml/L	80-120ml/L
MT-866A	100ml/L	80-120ml/L
MT-866B	(supplement use)	
Ni ²⁺	6g/L	5-8g/L
Temperature	45°C	40-50°C
pH value	8.5	8-9
Filtration	Continual filtration	
Agitation	Mechanical rabble	
STANDARD	0.5-0.8dm ² /L	

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,

Tianhe Dist., Guangzhou, China510665

TEL: +86 20 85576176/85555261/85555262

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com