



**GUANGZHOU MATEYS CHEMICALS LTD.**

**MT-830 Roughing & Conditioning Agent**

**1、 Specifications**

- (1) Chromic Acid + Sulphuric Acid
- (2) Mainly for surface roughing
- (3) Used in ABS, PC/ABS substrates

**2、 Compositions & Conditions**

Composition	First Roughing & Second Roughing
Chromiumtrioxide( $\text{CrO}_3$ )	380-400g/L
Sulfuric acid( $\text{H}_2\text{SO}_4$ )	200-220ml/L
$\text{Cr}^{3+}$	compositions $\leq 30\text{g/L}$ (perfect 6-9g/L)
Temperature	63-70°C (perfect 63-65°C)
Time	5-15mins (perfect 10mins)
Agitation	Mechanical rabble
Filtration	Recirculation filtration
Tank	Pd tank or steel tank with Pd inner

**Remarks. Pls kindly give us an email for more details.**

**ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,**

**Tianhe Dist., Guangzhou, China510665**

**TEL: +86 20 85576176/85555261/85555262**

**CEL: +86 13922181787 Skype: gzmateys**

**Email: [gzmateys@qq.com](mailto:gzmateys@qq.com) [gzmateys@163.com](mailto:gzmateys@163.com)**

**URL: [www.gzmateys.com/en](http://www.gzmateys.com/en) [gzmateys.en.alibaba.com](http://gzmateys.en.alibaba.com)**