



GUANGZHOU MATEYS CHEMICALS LTD.

FSN Tin Plating Anti-blushing Agent

1、 Specifications

- (1) Suitable for color resistance
- (2) Used in Tin plating post-treatment
- (3) Stable for long life
- (4) Robust on parts

2、 Composition & Conditions

Composition	Range
FSN	50ml/L
Temperature	50-70°C
Time	1-3 min
Work Flow: Sn Plating → Water Rinse → (Passivation) → Water Rinse → FSN → Water Rinse → Dry	

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,

Tianhe Dist., Guangzhou, China510665

TEL: +86 20 85576176/85555261/85555262

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com